

11 PRATS.

10/505334

DT09 Rec'd PCT/PTO 23 AUG 2004

DESCRIPTION

Method of Measuring Thermal Conductivity of Honeycomb  
Structure

5

Technical Field

The present invention relates to a method for measurement of thermal conductivity of a honeycomb structure, which can measure the thermal conductivity of a honeycomb structure in the shape of the honeycomb structure per se without preparing a test specimen or the like.

Background Art

Honeycomb structures (honeycomb filters) made of a ceramic are in use in order to capture the dust or another particulate matter contained in, for example, the exhaust gas emitted from automobiles (particularly, diesel engine automobiles) or the incineration gas generating during the incineration of waste, or to recover a product or a raw material from the high-temperature waste gas emitted in production processes of various industries. These honeycomb structures have a large number of through-holes surrounded by partition walls and extending in the axial direction of a honeycomb structure ; the partition walls surrounding the through-holes have a filtration ability; a given number of the through-holes are plugged at one end of a honeycomb structure and the remaining through-holes are plugged at the other end of a honeycomb structure ; thus, the honeycomb structures are formed so as to enable the capture and removal of the particulate matter contained in a dust-containing

fluid. The ceramic-made honeycomb structures are superior in heat resistance and corrosion resistance and have suitable properties as a filter material used in a high temperature, corrosive gas atmosphere and, therefore, are in use for  
5 purification of various exhaust or waste gases.

A high-temperature exhaust or waste gas is often passed through such a honeycomb structure and, in that case, the honeycomb structure generates a thermal strain in various forms depending upon its thermal conductivity. Hence, in  
10 designing a honeycomb structure, it is necessary to grasp its thermal conductivity. However, since the honeycomb structure has a special construction, there has heretofore been established no method for measuring the thermal conductivity of the honeycomb structure per se without preparing a test  
15 specimen or the like.

As the method for measuring the thermal conductivity of a fine ceramic, there is, for example, a laser flash method which is specified in JIS R 1611. This method has restrictions; for example, the method is restricted to a  
20 material having a porosity of 10% or less and also to a test specimen of flat plate having, for example, a square shape of 10 mm x 10 mm or less. Therefore, this method has been unable to apply to any honeycomb structure because of its material and shape. Further, the method has had an  
25 operational problem because a test specimen need be prepared.

The present invention has been made in view of the above-mentioned problems and aims at providing a method for measurement of thermal conductivity of a honeycomb structure , which can measure the thermal conductivity of a honeycomb  
30 structure in the shape of the honeycomb structure per se or

in a predetermined block shape without preparing, for example, a test specimen of particular shape.

#### Disclosure of the Invention

5           In order to achieve the above aim, the present invention provides the following method for measurement of thermal conductivity of a honeycomb structure .

[1]   A method for measurement of thermal conductivity of a honeycomb structure , the method comprising the steps of:

10           keeping the whole honeycomb structure in a steady temperature state with keeping two ends of the honeycomb structure at given different temperatures; and

          measuring a thermal conductivity of the honeycomb structure in the steady state.

15   [2]   The method for measurement of thermal conductivity of a honeycomb structure set forth in the above [1], wherein contact members kept at given different temperatures are contacted with the two ends of the honeycomb structure to keep the two ends of the honeycomb structure at given  
20   different temperatures.

[3]   The method for measurement of thermal conductivity of a honeycomb structure set forth in the above [2], wherein the thermal conductivity  $\lambda$  (W/mK) of the honeycomb structure is calculated from the following expression (1):

25           
$$\lambda = QH \cdot [L / (T1 - T2)] \quad (1)$$

          where the thermal conductivity  $\lambda$  (W/mK) of the honeycomb structure is specified in relation to:

          an amount of heat flow  $QH$  (W/m<sup>2</sup>) =  $[(Q1 + Q2)/2]$ , each of  $Q1$  (W/m<sup>2</sup>) and  $Q2$  (W/m<sup>2</sup>) being obtained by measuring an  
30   amount of heat flow at each contact member using a heat flow

meter connected with the contact member;

a distance  $L$  (m) between the two ends of the honeycomb structure; and

temperatures  $T_1$  (K) and  $T_2$  (K) of the two ends of the  
5 honeycomb structure in the steady temperature state of the whole honeycomb structure.

[4] The method for measurement of thermal conductivity of a honeycomb structure set forth in the above [2] or [3], wherein the two ends of the honeycomb structure and the  
10 contact members are contacted with each other via high-thermal-conductivity members.

[5] The method for measurement of thermal conductivity of a honeycomb structure set forth in the above [4], wherein a sheet having flexibility is used as the high-thermal-  
15 conductivity member.

[6] The method for measurement of thermal conductivity of a honeycomb structure set forth in the above [4] or [5], wherein the high-thermal-conductivity member is made of a film formed by applying a paste containing a substance of  
20 high thermal conductivity, on a contact face of the honeycomb structure and/or the contact member.

[7] The method for measurement of thermal conductivity of a honeycomb structure set forth in any of the above [2] to [6], wherein a contact pressure between the contact member and the  
25 end of the honeycomb structure is set at 1 to 10 kg/cm<sup>2</sup>.

[8] The method for measurement of thermal conductivity of a honeycomb structure set forth in any of the above [1] to [7], wherein an exposed portion of the side of the honeycomb structure is covered with a heat-insulating material.

30 [9] The method for measurement of thermal conductivity of a

honeycomb structure set forth in any of the above [1] to [8], wherein the honeycomb structure is made of a material having a thermal conductivity of 1 (W/mK) or more.

[10] The method for measurement of thermal conductivity of a honeycomb structure set forth in any of the above [1] to [9], wherein the honeycomb structure contains at least one kind selected from the group consisting of silicon carbide, a composite of silicon carbide and metallic silicon, and silicon nitride.

10

#### Brief Description of the Drawings

Fig. 1 is a side view showing a honeycomb structure and contact members which are in contact with the two ends of the honeycomb structure, in one embodiment of the method for measurement of thermal conductivity of a honeycomb structure according to the present invention.

Fig. 2 is a sectional view of a honeycomb structure, contact members, etc. along a plane including the axis of the honeycomb structure, in another embodiment of the method for measurement of thermal conductivity of a honeycomb structure according to the present invention.

#### Best Mode for Carrying Out the Invention

In the method for measurement of thermal conductivity of a honeycomb structure according to the present invention, the thermal conductivity of a honeycomb structure is measured with keeping the whole honeycomb structure in a steady temperature state; thereby, the thermal conductivity can be measured easily with, for example, a cylindrical honeycomb structure per se or a block of predetermined size cut out

therefrom, irrespective of the shape of the honeycomb structure to be measured and it is not necessary to prepare a test specimen of particular shape.

The embodiments of the present invention are described specifically below with reference to the accompanying drawings. However, the present invention is not restricted to the following embodiments and it should be construed that appropriate design changes, improvements, etc. can be added based on the ordinary knowledge of those skilled in the art, unless they deviate from the gist of the present invention.

Fig. 1 is a side view showing a honeycomb structure and contact members which are in contact with the two ends of the honeycomb structure, in one embodiment of the method for measurement of thermal conductivity of a honeycomb structure according to the present invention.

In the present embodiment, in order to measure the thermal conductivity of a honeycomb structure, at first, the two ends of the honeycomb structure in its axial direction are kept at given different temperatures. To achieve it, contact members 2 (21 and 22) kept at respective given temperatures are contacted with the two ends 11 and 12 of a honeycomb structure 1 in its axial direction, as shown in Fig. 1. By thus contacting the contact members 21 and 22 kept at respective given temperatures, with the two ends 11 and 12 of the honeycomb structure 1 in its axial direction, the two ends 11 and 12 can be kept at given different temperatures and thereby the whole honeycomb structure 1 can be kept in a steady temperature state.

Next, there is determined an amount of heat flow  $QH$  in the honeycomb structure 1 being kept in a steady temperature

state. The amount of heat flow  $Q_H$  is determined by measuring the amounts of heat flows  $Q_1$  and  $Q_2$  respectively flowing through the contact members 21 and 22 by the use of heat flow meters 3 (31 and 32) connected beforehand to the contact members 21 and 22 which are in contact with the two ends 11 and 12 of the honeycomb structure 1 in a steady temperature state and then making calculation using an expression of  $Q_H = (Q_1 + Q_2)/2$ .

In the present embodiment, the thermal conductivity  $\lambda$  (W/mK) of the honeycomb structure 1 is calculated from the following expression (1) wherein the thermal conductivity  $\lambda$  (W/mK) of the honeycomb structure is specified in relation to:

the above-obtained amount of heat flow  $Q_H$  (W/m<sup>2</sup>) [ $= (Q_1 + Q_2)/2$ ] in the honeycomb structure 1 in a steady temperature state,

a distance  $L$  (m) between the two ends of the honeycomb structure 1, and

temperatures  $T_1$  (K) and  $T_2$  (K) of the two ends 11 and 12 of the honeycomb structure 1 in the steady temperature state of the whole honeycomb structure.

$$\lambda = Q_H \cdot [L / (T_1 - T_2)] \quad (1)$$

Thus, measurement of thermal conductivity is made with the whole honeycomb structure being kept in a steady temperature state; therefore, the measurement of thermal conductivity can be made easily with, for example, a cylindrical honeycomb structure per se or a block of predetermined size cut out therefrom, irrespective of the

shape of the honeycomb structure to be measured and it is not necessary to prepare a test specimen of particular shape.

Such a method for measurement of thermal conductivity is called a steady method (JIS A 1412) but has not been  
5 applied to honeycomb structures.

In the present embodiment, it is preferred that the thermal contact between each end (11, 12) of the honeycomb structure 1 and each contact member (21, 22) is made as good as possible and the thermal conduction between the contact  
10 member 21 and the end 11 of the honeycomb structure 1 as well as between the end 12 of the honeycomb structure 1 and the contact member 22 is made as high as possible without heat loss. The losses of the amount of heat flow in these areas are regarded as indicating a barrier of the thermal  
15 conduction of the honeycomb structure per se and, therefore, may decrease the accuracy of measurement of the thermal conductivity of the honeycomb structure. For example, when, in the contact between the face of the end 11 of the honeycomb structure and the contact face 211 of the contact  
20 member 21, many (wide) gaps are formed owing to, for example, the fine surface unevennesses of the face and the contact face, thermal conduction may be difficult. Further, when the honeycomb structure is made of a material of high thermal conductivity, the decrease in the accuracy of measurement may  
25 be large.

For higher accuracy of measurement of thermal conductivity, it is preferred that the heat dissipation from the exposed portion of the side of the honeycomb structure 1 when a heat flows through the honeycomb structure 1, is as  
30 small as possible.



Fig. 2 is a sectional view of a honeycomb structure, contact members, etc. along a plane including the axis of the honeycomb structure, in another embodiment for carrying out the method for measurement of thermal conductivity of a  
5 honeycomb structure according to the present invention.

In order, as mentioned above, for the thermal contact between each end (11, 12) of the honeycomb structure 1 and each contact member (21, 22) to be made as good as possible and for the thermal conduction between the contact member 21 and the end 11 of the honeycomb structure 1 as well as  
10 between the end 12 of the honeycomb structure 1 and the contact member 22 to be made as high as possible with minimum heat loss, it was conducted, as shown in Fig. 2, to contact the contact member 21 with the end 11 of the honeycomb  
15 structure via a high-thermal-conductivity member 41 and contact the contact member 22 with the end 12 of the honeycomb structure via a high-thermal-conductivity member 42. By thus contacting each contact member (21, 22) with each end (11, 12) of the honeycomb structure via each high-thermal-  
20 conductivity member (41, 42), the gap formed in the contact between the face of the end 11 of the honeycomb structure and the contact face 211 of the contact member 21 owing to, for example, the fine surface unevennesses of the face and the contact face, becomes less because of the use of the high-  
25 thermal-conductivity member 4. Thereby, thermal conduction is improved and the measurement of thermal conductivity of a honeycomb structure can be made at higher accuracy. Since the high-thermal-conductivity member 4 has a high thermal conductivity, measurement of thermal conductivity of a  
30 honeycomb structure with the member 4 being present between

each end (11, 12) of a honeycomb structure and each contact member (21, 22) gives no large measurement error.

The high-thermal-conductivity member 4 is preferred to be a flexible sheet. This flexible sheet can be deformed  
5 into the shape of the above-mentioned gap formed between the two contact faces and can fill the gap, whereby good thermal conduction is obtained. As the material for the high-thermal-conductivity member 4 of a flexible sheet, there is preferred a carbon sheet or a metal foil of aluminum, copper  
10 or the like. The high-thermal conductivity member 4 is preferred to be as thin as possible relative to the test specimen used, in order to minimize the influence on measured thermal conductivity value. When the influence of the thickness of the high-thermal-conductivity member 4 on the  
15 measured thermal conductivity value  $\lambda$  is not negligible owing to the thickness relation of the high-thermal-conductivity member 4 and the test specimen (honeycomb structure 1), a corrected thermal conductivity  $\lambda_1$  (W/mK) of the test specimen (honeycomb structure 1) is calculated  
20 according to the following expression (2) using the thermal conductivity  $\lambda_2$  (W/mK) and thickness  $L_2$  (m) of the material for the high-thermal-conductivity member 4.

$$\lambda_1 = L_1 / [L / \lambda - L_2 / \lambda_2] \quad (2)$$

$\lambda$ : thermal conductivity (W/mK) of honeycomb structure

25  $\lambda_1$ : corrected thermal conductivity (W/mK) of honeycomb structure

$\lambda_2$ : thermal conductivity (W/mK) of  
high-thermal-conductivity member

$L$ : total thickness (m) of honeycomb structure and two  
30 high-thermal-conductivity members provided at two

end of honeycomb structure

L1: thickness (m) of honeycomb structure

L2: thickness (m) of high-thermal-conductivity member

The high-thermal-conductivity member 4 may be a film  
5 formed by applying, on the contact faces of the ends 11 and  
12 of the honeycomb structure, a paste containing a high-  
thermal-conductivity substance (powder) such as carbon,  
silver or the like (the paste is obtained, for example, by  
kneading the powder with an organic solvent represented by  
10 acetone). The paste may be applied on the contact face of the  
end (11, 12) of the honeycomb structure and/or on the contact  
face (211, 222) of each contact member (21, 22). By applying  
the paste, the gap formed between the above contact face can  
be filled as well and good thermal conduction can be obtained.

15 By setting the contact pressure when the contact member  
2 is in contact with the honeycomb structure 1 or with the  
high-thermal conductivity member 4, at 1 to 10 kg/cm<sup>2</sup>, the  
gap formed between the contact face can be filled and good  
thermal conduction can be obtained.

20 In the present embodiment, measurement of thermal  
conductivity can be made preferably when the honeycomb  
structure to be measured is made of a material having a  
thermal conductivity of 1 (W/mK) or more. Particularly when  
measurement of thermal conductivity is made using a high-  
25 thermal-conductivity member between a honeycomb structure and  
contact member, thermal conduction is good and the thermal  
conductivity of a honeycomb structure of high thermal  
conductivity can be measured at high accuracy. As preferable  
examples of the material for honeycomb structure, there can  
30 be mentioned silicon carbide, a composite material of silicon

carbide and metallic silicon, silicon nitride and non-oxides having a relatively high thermal conductivity. The method can preferably applied to oxides when they have a thermal conductivity of 1 W/mK or more.

5           In measurement of thermal conductivity of a honeycomb structure, it is also preferred that, as shown in Fig. 2, the exposed portion 13 of the side of a honeycomb structure 1 is covered with a heat-insulating material 5. Covering it with the heat-insulating material 5 suppresses heat dissipation  
10 from the exposed side portion 13 during measurement of thermal conductivity, whereby measurement of thermal conductivity can be made at high accuracy. As the heat-insulating material, there can be mentioned, for example, a polyurethane mat and a polystyrene foam. The area to be  
15 covered with the heat-insulating material may be not only the exposed side portion 13 but also the whole portion including the contact members 2. It is also preferred to surround the honeycomb structure with the honeycomb structures made of the same material in place of using the heat-insulating material,  
20 because it is effective for making homogeneous the heat flow in the honeycomb structure.

#### Examples

The present invention is described more specifically by way of Examples. However, the present invention is not  
25 restricted to these Examples.

(Examples 1 to 7)

There were produced, by ordinary extrusion molding, two kinds of honeycomb structures made of metallic silicon-bonded silicon carbide (silicon carbide bonded with metallic  
30 silicon) and having a rib thickness of 15 mil and a cell

density of 200 cpsi (cells per square inch) or 300 cpsi.

A block of 35 mm x 35 mm x 25 mm was cut out from each of the two kinds of honeycomb structures and measured for thermal conductivity by a steady method, using neither high-  
5 thermal-conductivity member nor heat-insulating material, as shown in Fig. 1. Each block was measured for thermal conductivity by the steady method using both or either of high-thermal-conductivity members and a heat-insulating material, as shown in Fig. 2. The results are shown in Table  
10 1.

Table 1

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7
High-thermal-conductivity member	Not used	Carbon sheet	Not used	Aluminum foil	Carbon sheet	Not used	Carbon sheet
Heat-insulating material	Not used	Not used	Polystyrene foam	Not used	Polystyrene foam	Not used	Polystyrene foam
Cell density (cpsi)	200	200	200	200	200	300	300
Opening ratio (%)	62	62	62	62	62	55	55
Effective area ratio (%)	38	38	38	38	38	45	45
Thermal conductivity, converted value (W/mK)	11	11	11	11	11	14	14
Thermal conductivity, measured value (W/mK)	4	12	8	8	12	6	15

Here, thermal conductivity, converted value means a value obtained by measuring the thermal conductivity of a honeycomb structure by the laser flash method based on JIS R 1611, using a test specimen of particular shape and then  
5 multiplying the measured thermal conductivity by an effective area ratio which indicates an effective end face area obtained by subtracting the total opening area of the end face of the honeycomb structure from the area of the end face, to convert the measured thermal conductivity into the thermal  
10 conductivity of the honeycomb structure per se. The thermal conductivity of a honeycomb structure measured by the laser flash method includes an error associated with the porosity, etc. but has certain accuracy; therefore, the measured thermal conductivity in the present Examples was evaluated in  
15 comparison with the thermal conductivity measured by the laser flash method.

As shown in Table 1, the thermal conductivity of a honeycomb structure can be measured by a steady temperature method. As indicated in Examples 1 and 6, the measurement of  
20 thermal conductivity is possible even when neither high-thermal-conductivity member nor heat-insulating material is used; however, a value nearer to that of the laser flash method is obtainable by using an aluminum foil or a carbon sheet as high-thermal-conductivity members or a polystyrene  
25 foam as a heat-insulating material (Examples 2 to 5 and 7).

In the present Examples, preparation of a flat plate of 10 mm x 10 mm x 1 mm or less is not necessary and measurement of thermal conductivity can be made using a test specimen of block shape; therefore, workability of sample preparation is  
30 improved and the time for sample preparation is shortened.

### Industrial Applicability

As described above, according to the present method for measurement of thermal conductivity of a honeycomb structure ,  
5 measurement is possible in a shape of a honeycomb structure per se or in a block shape and preparation of, for example, a test specimen of particular shape is not necessary. As a result, the operability of thermal conductivity measurement is improved and the time for sample preparation (processing)  
10 is shortened.